






TECHNICAL DATA SHEET - CST 0300/01 - 23/07/2003

N 2609

(*)				
T	°C	-50 +250		
p	bar	60	40	20
V	m/s	1	3	10
pH		4 ÷ 10		



(*) Do not use the product to the maximum temperature and pressure associated without consulting the manufacturer

Composition

- Pre oxidized/synthetic yarn
- Graphite impregnation
- Lubricant

Features

CARRARA N 2609 has been developed for the purpose of creating packing totally free from asbestos at a very competitive price.

Made of synthetic composite fibre at the intermediate pre oxidized carbon stage, than impregnated with graphite and a lubricant for high temperatures, free from silicone.

Applications

Oils, steam, alcohol light solvents, acids and alkalis.

size mm	size inch	kg/box	lbs/box	mt/box	ft/box	mt/kg	ft/lbs
3,0	1/8	1,0	2,2	92,6	304	92,6	137,9
4,0	-	1,0	2,2	52,1	171	52,1	77,6
5,0	3/16	1,0	2,2	33,3	109	33,3	49,7
6,0	-	2,5	5,5	57,9	190	23,1	34,5
6,5	1/4	2,5	5,5	49,3	162	19,7	29,4
8,0	5/16	2,5	5,5	32,6	107	13,0	19,4
9,5	3/8	2,5	5,5	23,1	76	9,2	13,8
10,0	-	2,5	5,5	20,8	68	8,3	12,4
11,0	7/16	2,5	5,5	17,2	56	6,9	10,3
12,0	-	2,5	5,5	14,5	47	5,8	8,6
12,7	1/2	2,5	5,5	12,9	42	5,2	7,7
14,0	9/16	5,0	11,0	21,3	70	4,3	6,3
16,0	5/8	5,0	11,0	16,3	53	3,3	4,8
17,5	11/16	5,0	11,0	13,6	45	2,7	4,1
18,0	-	5,0	11,0	12,9	42	2,6	3,8
19,0	3/4	5,0	11,0	11,5	38	2,3	3,4
22,0	7/8	5,0	11,0	8,6	28	1,7	2,6
25,5	1	5,0	11,0	6,4	21	1,3	1,9
Packaged +/- 10% in weight							